

Code	Description	Size	Colour
23105	Gorilla Solvent Based Wallboard Adhesive	375ml	Beige

1. Description

Gorilla Solvent Based Wallboard Adhesive is a one component, high performance, paste like construction adhesive formulated to bond a variety of common construction materials from timber, many metals

2. Characteristics

- Strong Lasting Bond
- Suitable for bonding on uneven surfaces
- Will not sag or go stringy
- Designed to bond to wide range of substrates
- Suitable for interior/exterior use
- Suitable for the bonding of Polystyrene

3. Technical Data

Type:	SBR Rubber
Colour:	Beige
Curing System;	Physical Drying & Crystallation
Curing Speed: (*)	Hand Tight in Ca. 20min
Application Temperature:	5°C to +30°C
Service Temperature:	-20°C to +60°C
Open Time: (*)	Ca. 15 min

**This varies according to ambient conditions such as temperature, humidity, substrate etc*

4. Applications

- Bonding in the renovation industry
- General bonding in the construction industry
- All bonding in various assemblies
- Bonding of cable trays and panels
- Materials
 - Timber Framing
 - Gypsum Wallboard
 - Concrete/Masonry
 - Galvanized Iron
 - (ACM) Aluminum Composite
 - Foamed Polystyrene
 - Bonding of PVC Shower Linings
 - Bonding of Acrylic Shower Linings

5. Packaging

375ml

6. Shelf Life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C on a wooden pallet and kept from freezing. Keep out of direct sunlight and away from sources of heat.

7. Application Instructions

Surfaces:	All usual surfaces.
State of Surface:	Clean, dry and free of dust and grease.
Clean Up	with Solvent Cleaner Immediately after use

Application

- Method:
1. Surfaces must be clean, dry, and free of dirt, grease, oil & water.
 1. Apply a bead of Accent Construction Adhesive along the length of the substrate.
 2. Nail, clamp or screw to hold load and ensure direct contact adhesion.
 3. Wait at least 24hours before removing clamps or fasteners.
 4. For Polystyrene:
 - a. Apply adhesive to the surface
 - b. Press both parts together immediately
 - c. Pull apart and separate for 10-15 min.
 - d. After, press bond again and support if necessary

Soudal Ltd recommends a preliminary compatibility test to ensure that the user is satisfied with the result given.

8. Limitations

The Gorilla Construction Solvent Based Adhesive sets to a rigid bond. If a flexible bond is required the user should consider the Fix All There is no adhesion to the following types of substrates of PE, PP, PTFE (Teflon) and Bituminous substrates. Soudal Ltd recommends a preliminary test for compatibility to ensure that you get the desired result.

9. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- Please refer to MSDS for more detailed information

Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email sales@soudal.co.nz.***

Last Updated: 13 January 2020

Recommended use:		
HSNO Group Standard		
UN number, shipping name and packaging group:		
Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	14 Avalon Drive	Phone: (07) 847 5540
	Nawton	Fax: (07) 847 0324
	Hamilton 3200	Email: sales@holdfast.co.nz
	New Zealand	Website: www.holdfast.co.nz
POISON CENTRE NUMBER: 0800 764 766 (24 hours)		