

Code	Description	Size	Colour
09188	Holdfast Ultrabonder 909	20gr	Black

## 1. Description

Holdfast Ultrabonder 909 is a black, thermal resistant, instant adhesive gel. It has been specially formulated to provide impact, peel and improved resistance to heat, humidity or damp conditions, which can be used for virtually any type of fastening job. It has been specially formulated to achieve the strongest possible bond between well-mated, non-porous surfaces, such as rubber, metals, plastics, glass, etc..

## 2. Characteristics

- High strength
- Fast setting/fixing adhesive
- One component
- Solvent-free
- Does not require use of catalyst, heat or clamps

## 3. Technical Data

<b>Base:</b>	Ethyl Cyanoacrylate
<b>Colour:</b>	Black
<b>Specific Gravity (20 °C):</b>	1.05
<b>Flash Point (°C):</b>	70(158 F)
<b>Boiling Point (°C):</b>	65-6 mmHg
<b>Viscosity (cps):</b>	Gel
<b>Softening Point (°C):</b>	130 (266°F)
<b>Dielectric Constant (at 10MHz):</b>	3.30
<b>Dielectric Loss (at 10MHz):</b>	0.04

## 4. Applications

- Ceramics/Tiles
- Hardwood
- Laminated plastics
- Metals
- Paper
- Foam plastics
- Some PVC
- Other non-porous surfaces (\*\* Test Dependant)

## 5. Packaging

20g

## 6. Shelf Life

12 months

## 7. Application Instructions

Method:

1. Make sure the surfaces to be bonded are clean and dry (preferable to solvent wipe plastics, glass, and rubber, and to acid-treat metals).
2. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film after compression.
3. Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute. (Max strength is achieved in 24 to 48 hours).
4. Wipe off excess adhesive from the top of the container and recap. If left uncapped, may deteriorate by contamination from moisture in the air.
5. Because Gorilla Ultrabonder 909 condenses by polymerization, sometimes whitening will occur on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with acetone.

### Bond Strength

(Tensile Shear Strength, Cured for 24 Hours at 20-25°C)

	KG/CM2		KG/CM2
Rigid PVC to Rigid PVC	40-60	SBR to SBR	5-10
ABS to ABS	50-70	Steel to Steel	190-210
Polycarbonate to Polycarbonate	80-120	Stainless Steel to Stainless Steel	160-180
Polystyrene to Polystyrene	30-45	Aluminium to Aluminium	170-190
Natural rubber to Natural rubber	5-9	Copper to Copper	150-170
*Neoprene to Neoprene	5-9	Steel to Rigid PVC	50-60
NBR to NBR.....	5-9	Stainless Steel to Neoprene	5-10
ABS to SBR.....	5-10		

### Cure Speed

	Seconds		Seconds
ABS to ABS	15-25	NBR to NBR	10-15
Wood to Wood	>90	Stainless Steel to Stainless Steel	>90
ABS to Stainless Steel	60-75	ABS to NBR	15-20
NBR to Stainless Steel	> 90	Wood to ABS	>90

### Precaution

- Use with proper ventilation. Avoid contact with skin and eyes.
- If contact with skin occurs, rinse with warm water or dissolve gradually with appropriate debonder. Do not try to remove forcibly.
- If adhesive gets into eye, keep eye open and rinse thoroughly. Seek medical attention immediately.
- Keep well out of reach of children.
- Keep adhesive in a cool, dry place 20-25°C. For long term storage, refrigeration (5°C) is recommended.

Holdfast	Competitor	Properties
105	420	20g Low viscosity, general industrial grade cyanoacrylate adhesive. Penetrating Gorilla Super Glue Adhesive
		500g Fast, strong bonds to a wide range of metal, plastic and rubber materials.
108	420	20g Low viscosity, general industrial grade cyanoacrylate adhesive. Penetrating.
		500g Fast, strong bonds to a wide range of metal, plastic and rubber materials. (Available upon request)
401	*401	20g Medium viscosity fast curing cyanoacrylate adhesive.
		500g For rubber and plastic components (Available upon request)
403	414	20g Medium viscosity cyanoacrylate adhesive
		500g For Vinyl and other plastics (Available upon request)
407	444	20g Medium viscosity cyanoacrylate adhesive Gorilla Super Glue Adhesive
		500g Electronic applications
412	416	20g Higher viscosity cyanoacrylate adhesive
		500g Strong bonds to a wide range of metal, plastic and rubber materials. (Available upon request)

<b>1417</b>	417	20g	Temporary bonding cyanoacrylate adhesive (Available upon request)
<b>424</b>	422	20g	High viscosity, general industrial grade cyanoacrylate adhesive Gorilla Super Glue Adhesive.
		500g	Bonding a wide range of metal, plastic and rubber materials.
<b>909</b>	409	20g	Gel cyanoacrylate adhesive. Non-drip, nor-run applications Gorilla Super Glue Adhesive
		500g	
<b>C681</b>		20g	Clear, high viscosity rubber toughened cyanoacrylate adhesive. Impact,
		1kg	& Peel resistance (Available upon request)
<b>C685</b>	411	20g	Clear, high viscosity rubber toughened cyanoacrylate adhesive. Impact,
		1kg	& Peel resistance (Available upon request)
<b>B680</b>	480	20g	Black, medium viscosity cyanoacrylate adhesive. Flexible.
		500g	Good peel strength. Bonds metal, plastic & rubber. (Available upon request)
<b>B684</b>	410	20g	Black, rubber toughened cyanoacrylate adhesive. Peel & Impact resistant.
		500g	Bonds metal, plastic & rubber. (Available upon request)
<b>B689(Gel)</b>	426	20g	Black cyanoacrylate gel adhesive. Impact, peel & moisture resistant. (Available upon request)
<b>B299(Gel)</b>	*455	20g	Black gel, low odor, non-blooming cyanoacrylate adhesive. (Available upon request)
<b>601</b>	401	20g	Med. viscosity, difficult surface industrial grade cyanoacrylate adhesive. Gorilla Super Glue .
		500g	Fast, strong bonds to a wide range of metal, plastic and rubber materials.
<b>606</b>	406	20g	Low viscosity, difficult surface industrial grade cyanoacrylate adhesive.
		500g	Fast, strong bonds to a wide range of plastic and rubber & EPDM materials. (Available upon request)
<b>695</b>	495	20g	Med. viscosity, difficult surface industrial grade cyanoacrylate adhesive.
		500g	Fast, strong bonds to a wide range of metal, plastic and rubber materials. (Available upon request)
<b>701</b>	493	20g	Low viscosity general industrial grade cyanoacrylate adhesive.
		500g	For close fitting Metal bonding (Available upon request)
<b>703</b>	496	20g	Medium viscosity, fast setting cyanoacrylate adhesive.
		500g	For metal bonding (Available upon request)
<b>724</b>	415	20g	General Industrial grade cyanoacrylate adhesive for metal bonding
		500g	Realignment requirements, irregular surfaces, metal bonding (Available upon request)
<b>201</b>	408	20g	Low viscosity, low odor, non-blooming cyanoacrylate adhesive. (Available upon request)
		500g	
<b>202</b>	460	20g	Low viscosity, low odor, non-blooming cyanoacrylate adhesive.
		500g	Bonds a wide variety of materials for cosmetic applications. (Available upon request)
<b>212</b>	403	20g	Medium viscosity, low odor cyanoacrylate adhesive.
		500g	Bonds a wide variety of materials for low blooming applications. (Available upon request)
<b>209</b>	455	20g	Low odor, low blooming gel cyanoacrylate adhesive. (Available upon request)
<b>TB601</b>	4210	20g	Black, low viscosity rubber toughened cyanoacrylate adhesive. Impact, Peel & Thermal resistance (Available upon request)
<b>T698</b>	498	20g	Medium viscosity cyanoacrylate adhesive – resists Thermal cycling to 250F (Available upon request)
<b>TB625</b>	4211	20g	Black, high viscosity rubber toughened cyanoacrylate adhesive. Impact, Peel Humidity & Thermal resistance (Available upon request)
<b>TB909</b>	*4205	20g	Black, rubber toughened cyanoacrylate gel adhesive. Impact, Peel Humidity & Thermal resistance (Available upon request)

<b>MX-2100</b>	770	500g	PP. PE PRIMER (Available upon request)
<b>MX-2001L</b>	7452	500g	LIQUID ACCELERATOR (Available upon request)
<b>MX-2201</b>	768	500g	DEBONDER (Available upon request)

## 8. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- Wear gloves and safety goggles.

### **Remark**

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email [sales@soudal.co.nz](mailto:sales@soudal.co.nz).***

**Last Updated:** 31 July 2019

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	14 Avalon Drive	Phone: (07) 847 5540
	Nawton	Fax: (07) 847 0324
	Hamilton 3200	Email: <a href="mailto:sales@soudal.co.nz">sales@soudal.co.nz</a>
	New Zealand	Website: <a href="http://www.soudal.co.nz">www.soudal.co.nz</a>