

Code	Description	Size	Colour
172130	Soudal Pureseal PVC Priming Fluid	250 ml	Red
172131	Soudal Pureseal PVC Priming Fluid	500 ml	Red
172132	Soudal Pureseal PVC Priming Fluid	1 Litre	Red
172133	Soudal Pureseal PVC Priming Fluid	5 Litre	Red

1. Description

Pureseal PVC Priming Fluid is a high-quality, low-VOC, fast acting primer compatible with Pureseal PVC Pipe Cement Type N and P for jointing PVC pipes and fittings.

2. Characteristics

- Ready to Use and no mixing required
- Fast acting
- WaterMark Certified: WM-032290
- Conforms to AS2216 – Packaging for poisonous substances
- Colour-coded lid for product identification

3. Technical Data

Basis	Hydrocarbon Liquids
Consistency	Medium Bodied
Density	Ca. 0.841 g/ml
Viscosity (Brookfield)*	Water thin @ 23°C
Application Temperature	5°C to +30°C

* This value may vary depending on environmental factors such as temperature, moisture & type of substrate.

** This information relates to fully cured product.

4. Applications

- Soffen and prime PVC pipes and fittings for non-pressure and pressure application in the installation of plumbing fixtures and for electrical applications.

5. Shelf Life

36 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.
Keep out of direct sunlight and away from sources of heat.

6. Application Instructions

Substrates: Pressure & Non-pressure PVC pipes and fittings
Nature: Rigid, clean, dry, free of dust and grease.
Surface Preparation: Pureseal PVC Priming Fluid must be used before Pureseal PVC Pipe Cement Type P & Pureseal PVC Pipe Cement Type N is applied.

Application Method

Applicator:

Applicator dauber attached to the supplied cap on the bottle

Note: Jointed pipes and fittings can only be removed mechanically.

The jointing procedure must comply with AS/NZS 2032 requirements and is intended for skilled individuals to carry out the work.

Preparation:

1. Check pipe type.
2. Cut pipe square and deburr both inside & outside of pipe.
3. Check the dry fit of pipe and fittings & correct interference fit. The pipe should easily go 1/3 of the way into the fitting.
4. Avoid mixing with other solvents/additives to the priming fluid or PVC Pipe Cement.
5. With fitting fully engaged, mark with a pencil, not score, the pipe. Pureseal PVC Priming Fluid should be applied evenly, slightly beyond the marked witness line.
6. Use PVC Pipe Cement **Type P for Pressure joints**.
Use PVC Pipe Cement **Type N for Non-pressure joints**.

8. Remarks & Limitations

- Always tightly close the packaging with the appropriate lid to avoid solvent evaporation.
- PVC Pipe cement must never be used in PVC or CPVC piping systems using or being tested by compressed air or gases; including air-over-water booster. Please do not use it in conjunction with flue gas ventilation systems.
- It is highly recommended that the installer review the instructions supplied by the pipe and fitting manufacturer.
- Use with caution. Spillage can result in damage to surfaces.
- Temperature can affect the setting time of Primer and PVC Pipe Cements. At lower temperatures, the setting time is longer, while at higher temperatures, it is quicker. Temperatures greater than 30°C will result in rapid evaporation of the solvent before the solvents can penetrate the pipe surfaces. This may lead to an unsatisfactory bond with a dry joint resulting in a failed bond. Always re-coat the pipe and fitting if the adhesive dries during application.
- For larger-size pipes, requires a larger application brush, contact the Technical Service Department for recommendations.
- Colour stains are permanent, however the colour may fade over time in direct sunlight.
- No additives of any kind shall be mixed with these solvent cement and priming fluids.

VOC content information

- "[Pipe cements are not relevant to the VOC credit as they have little influence on indoor air quality. Plumbing pipes are usually installed sometime before building occupation and any residual of solvent will be negligible by the time the building is sealed and occupied.
- In addition, plumbing pipes are not a major component of an individual fit-out or building, plumbing cements are minor in quantity in the indoor fit-out when compared to adhesives used in countless other indoor applications.]"
- Refer to Green Building Council Australia (GBCA) website for further details <https://www.gbca.au/>.

8. Certificates & Standards

- WaterMark certified: WM-032290
- Meets the requirement for AS/NZS 3879
- Meets the requirement for AS/NZS 4020
- Meets the requirement for AS2216 – Packaging for poisonous substances

9. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- Please refer to SDS for more detailed information at www.soudal.co.nz
- Use only in a well ventilated place.

Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email info@soudal.co.nz.***

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	134 Kohia Drive	Phone: (07) 847 5540
	Horotiu	
	Hamilton 3288	Email: info@soudal.co.nz
	New Zealand	Website: www.soudal.co.nz