

Code	Description	Size	Colour
19270	Gorilla Ultra Rapid Gap Filler	350 gr	White
19271	Gorilla Ultra Rapid Gap Filler	750 gr	White

## 1. Description

Gorilla Ultra Rapid Gap Filler is a multi-purpose ready mixed high quality compound for filling gaps and cracks in timber, concrete, plaster, and stone.

## 2. Characteristics

- Interior/exterior finish with excellent water resistance.
- No cracking up to 6 mm and minimal shrinkage.
- It can be nailed, screwed easily without cracking.
- Almost odour free

## 3. Technical Data

<b>Base:</b>	Acrylic resins
<b>Odour:</b>	Wet-Low; Dry-None
<b>Consistency:</b>	Paste
<b>Density:</b>	Approx. 1.2-1.3 g/ml (DIN 53479B)
<b>Solids Content:</b>	76-77%
<b>Curing Rate (*):</b>	60 - 90 minutes for 1 mm film thickness on plain timber at 25°C. 30 minutes for thinner film.
<b>Sandability:</b>	Excellent
<b>Elastic Recovery:</b>	Limited
<b>Application:</b>	Smooth firm paste for better tooling 19270 305gr makes 290ml 19271 750gr makes 625ml

*\*This varies according to ambient conditions such as temperature, humidity, substrate etc*

## 4. Applications

- Filling of gaps in timber, concrete, plaster & stone.

## 5. Packaging

350 gm & 750 gm pottle

## 6. Shelf Life

6 months in unopened packaging in a cool and dry storage place. Protect against frost.

## 7. Application Instructions

Method: Manual  
 Application Temperature: +5°C until +30°C  
 Clean: Water immediately after use

Repair: Gorilla Ultra Rapid Gap Filler

### Surfaces

Type: All usual building substrates

State: Surfaces must be clean, dry and sound.

Preparation: Prepare surfaces by sanding and wiping to remove sanding dust.

### Application

- All surfaces must be clean, dry and free from dust or grease.
- Using a putty knife or spatula press Light Weight Filler into the cracks or holes to be filled. Each layer may be up to about 6 mm thick. Allow to dry between layers if over 6 mm.
- Once filler is dry, sand smooth and paint with water or solvent based paint, following the manufacturer's recommendations. An undercoat is recommended to give smoother finish.
- Do not use Light Weight Filler in conditions where it will be continuously wet. No suitable for joints where movement will occur.
- If too stiff due to exposure or drying, add a small amount of water, a bit at a time mixing between additions to bring it to a useable consistency.

Pre-testing for adhesion is intended to eliminate potential field problems. This testing will aid in determining the proper surface preparation method.

### Joint Size

Depth: 1-6mm (if depth is over this allow to dry completely between fillings)

Holdfast recommends preliminary compatibility tests

## 8. Health and Safety Recommendation

- Apply the usual industrial hygiene
- Please refer to the MSDS for more detailed information.

### Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email [sales@soudal.co.nz](mailto:sales@soudal.co.nz).***

**Last Updated:** 29 July 2019

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	14 Avalon Drive	Phone: (07) 847 5540
	Nawton	Fax: (07) 847 0324
	Hamilton 3200	Email: <a href="mailto:sales@soudal.co.nz">sales@soudal.co.nz</a>
	New Zealand	Website: <a href="http://www.soudal.co.nz">www.soudal.co.nz</a>