

Code	Description	Size	Colour
19288	Gorilla Grip 10 Minute Cure Construction Adhesive	310ml	Translucent

1. Description

Gorilla Grip is single-component, ready to use, translucent, polyurethane based construction adhesive.

2. Characteristics

- Can be applied with a caulking gun
- Professional quality
- Fast Curing
- Paintable
- Expands as curing to fill uneven surfaces within the band line
- Non staining on porous substrates
- Water resistance D4
- Solvent free

3. Technical Data

Base:	Polyurethane
Consistency:	Paste
Curing System:	Moisture Cure
Open time (*)	Approx. 10 minutes
Clamping Time*	10 minutes
Curing time (*)	10 minutes
Specific Gravity	ca. 1.11 g/ml
Temperature Resistance	-30°C until + 100°C after curing
Water Resistance (EN204)	D4
Shear Strength (EN204)	> 10 N/mm ²
Solid Content	100% (Solvent Free)
VOC(%)	0%
VOC (g/litre)	0

*This varies according to ambient conditions such as temperature, humidity, substrate etc

4. Applications

- To fix battens, windowsills, skirting boards, coving, plasterboard
- Gluing carpet grippers, edge strips and stair nosing's
- Bonding of wall and floorboards, window frames and partitions
- Interior applications with frequent long-term exposure to running or condensed water
- Exterior applications with exposure to weather influences
- Manufacturing of door and window-frames that need to meet class D4 according to EN204
- Bonding of wooden construction elements
- Bonding of insulation materials (including polystyrene)
- For masonry bonding

5. Packaging

310ml Cartridge

6. Shelf Life

15 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

7. Building Product Information

Manufactured By Soudal NV
Distributed By Soudal Ltd

Relevant Building Code Clauses

Note: This product is an adhesive and on its own is not within the scope of the NZ Building Code. However, when it is used as part of an internal floor, wall, or ceiling system, or with other building elements that must comply with the NZ Building Code, and it is used in accordance with that material supplier's specification and Soudal's technical literature, it will contribute to meeting the requirements of the following clauses:

- B1 Structure: Performance clauses B1.3.1, B1.3.2, B1.3.3 (a, b, j, q), B1.3.4
- B2 Durability: Performance clauses B2.3.1 - (b) not less than 15 Years, (c) not less than 5 years
- F2 Hazardous Building Materials: Performance clause F2.3.1

Contribution to compliance With NZBC

Performance B1.3.1, B1.3.2, B1.3.3 (a, b, j, q) B1.3.4: When used as an adhesive this product contributes to meeting the loading requirements that bonded lining elements are subjected to, as a result of self-weight, imposed in-use gravity loading, impact, and the effects of creep and shrinkage over time.

Performance B2.3.1 (b) 15 years and (c) 5 years: This product achieves these durability requirements and will remain serviceable for 15 years, or more, when installed and maintained in accordance with the relevant Soudal product technical documents. Soudal maintains production & management systems in accordance within its ISO9001:2015 Quality Management System.

Performance F2.3.1: This product meets this requirement when used and applied in accordance with Soudal's installation instructions and does not present a health hazard to people occupying or using the building. Refer to the Soudal Product Technical Data Sheet and product Safety Data Sheet soudal.co.nz for further information if required.

8. Application Instructions

Surfaces

Type: Various porous surfaces such as wood, concrete, stone and other materials commonly used in construction. Not suitable for polyethylene and polypropylene
State: Clean, dry, free of grease and loose particles.
Pre-treatment: Moisture in the air or the substrates will cure the adhesive, which will foam slightly. Slightly moistening the substrates will speed up the cure and increase the filling properties of the adhesive. Adhesion to metal batons is determined by surface preparation.

Application

Method: Apply the adhesive by means of a caulking gun to one of the substrates. Join the two parts together and clamp for at least 15 minutes. Clamping the joined parts is necessary to achieve high bond strength.
Application Temperature: +5°C to +35°C
Clean: Before curing from tools and materials, with Gorilla Solvent Cleaner.
Repair: Cured adhesive has to be removed mechanically.
With Gorilla Grip® 10 Minute Cure Construction Adhesive.

Soudal recommends preliminary compatibility tests on surfaces on which Gorilla Grip® 10 Minute Cure Construction Adhesive have not been applied previously.

Limitations

- Gorilla Grip 10 Minute Cure Construction Adhesive can be applied to a wide variety of substrates. Due to the fact that specific substrates may differ from Supplier to Supplier, we recommend preliminary compatibility tests.
- Gorilla Grip 10 Minute Cure Construction Adhesive requires two (semi) porous surfaces to work successfully.
- As some timber treatments contain wax it is recommended that the surface of these timbers is activated with Gorilla 696 Surface Activator before application of adhesive.
- Soudal Gorilla Grip® is not considered a structural or load bearing adhesive. If unsure about your application please consult Soudal New Zealand technical services

9. Health and Safety Recommendation

- Wear Gloves
- Apply the usual industrial hygiene
- Please refer to the MSDS for more detailed information.

Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email info@soudal.co.nz.***

Last Updated: 15 April 2024

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	134 Kohia Drive	Phone: (07) 847 5540
	Horotiu	
	Hamilton 3288	Email: info@soudal.co.nz
	New Zealand	Website: www.soudal.co.nz