

Code	Description	Size	Colour
20165	Gorilla Firesil Silicone	310ml	Grey

1. Description

Gorilla Firesil Silicone is a high quality, neutral, elastic, one-component sealant based on silicones which conforms to the DIN4102 B1 standard for fire retardancy and has a fire rating of up to 4 hours in certain joint configurations (EN 1366 part 4 – NN713.020 – BS 476/20).

2. Characteristics

- Very easy to apply
- Colourfast and UV-resistant
- Remains permanently elastic after full cure
- Very good adhesion on most surfaces
- Low modulus
- DIN 4102-Part 2: Class B1
- Up to 4 hours fire rating with normal PE Backing material – refer to www.soudal.co.nz for specific details

3. Technical Data

Base:	Polysiloxane
Consistency:	Stable Paste
Curing System:	Moisture Cure
Skin Forming:	Ca 20 min. (20°C/65% R.H)
Curing Rate:	1mm/24h
Shore A Hardness:	16 Shore A
Specific Gravity:	Ca 1,17g/cm ³
Temperature Resistance:	-40°C until +140°C
Elongation at Break:	900% (DIN52455)
E-Modulus 100%:	0,20N/mm ² (DIN52455)
Elastical Recovery:	>90% (DIN52455)
Maximum Deformation:	+25%

* This can vary according to environmental circumstances such as temperature, humidity, substrate, etc.

4. Applications

- All linear building and glazing joints which require a fire rating
- Fire rated expansion joints

5. Packaging

Cartridge 310ml (net content)

6. Shelf Life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C. Do not expose to frost.

7. Building Product Information

Manufactured By	Soudal NV
Distributed By	Soudal Ltd

Relevant Building Code Clauses

- Clause B2 DURABILITY: Performance B2.3.1 (b) 15 years and B2.3.1 (c) 5 years
- Clause C3 Fire Affecting Areas Beyond the Fire Source. Performance clauses C3.1, C3.2, C3.3
- Clause E2 EXTERNAL MOISTURE: Performance E2.3.2.
- Clause F2 HAZARDOUS BUILDING MATERIALS: Performance F2.3.1.

Contribution to compliance With NZBC

Performance B2.3.1 (b) 15 years and (c) 5 years: This product achieves these durability requirements and will remain serviceable for 15 years, or more, when installed and maintained in accordance with the relevant Soudal product technical information. soudal.co.nz. Soudal maintains management and production records within its ISO9001:2015 Quality Management System.

Performance C3.1, C3.2, C3.3: This product has been fire tested in various combinations of sealed joints and /or penetrations with different dimensions and different building components. It contributes to meeting the requirements of C3 only when used in these tested combinations. All fire-rated joints must be designed and specified by a registered fire engineer. For more information, such as test certificates, refer to soudal.co.nz.

Performance E2.3.1, E2.3.2: In accordance with E2/AS1 and E2/AS3 (CCANZ CP 01:2014) this product has been tested and is compliant with the ISO11600:2002 Type F, Class 25LM classification, soudal.co.nz. When used to seal flexible joints, as part of a wall cladding system, or around external openings, such as windows and doors, the product contributes to meeting the E2.3.1 and E2.3.2 weather-tightness requirements.

Performance F2.3.1: This product meets this requirement when used and applied in accordance with Soudal's product installation instructions and does not present a health hazard to people occupying or using the building. Refer to the Soudal Product Technical Data sheet and product Safety Data Sheet soudal.co.nz for further information if required.

8. Application Instructions

Surfaces

Type:	All usual porous and non-porous building materials
State:	Clean, dry, free of dust and grease
Preparation:	Porous substrates; Surfaces such as lightweight aerated concrete, masonry plasters and other surfaces regarded as very porous should be primed with Primer 150. Non-porous substrates; due to the wide range of materials, coatings and surface finishes we recommend to test to verify adhesion to determine the correct adhesion promoter. Preparing the surface with Gorilla 696 Surface Activator will maximise adhesion.

Due to the range of substrates on the market recommend preliminary compatibility tests prior to commencement of application.

Joint Size

Minimum Width:	5mm
Maximum Width:	30mm
Joint Configuration:	width = 2xdepth

Application

Method:	Caulking Gun
Backing Material:	PE backer rods for correct joint dimension
Application Temperature:	+1°C to +30°C
Clean:	With Gorilla Solvent Cleaner
Repair:	With Gorilla Firesil Silicone
Finish:	With soapy solution

Approvals

- to AS1530.4 and AS4072.1
- EWFA Report No. 23751-02
- EWFA Report No. 45717-02
- Various applications with fire doors

Linier Joints – Vertical & Horizontal – Aerated Concrete

Wall Thickness (mm)	Gap Width (mm)	Seal Depth (mm)	Backing Material	Seal	FRL
200	10	10	Gorilla PEF	Exposed	-/240/240

Linier Joints – Vertical – Aerated Concrete

Wall Thickness (mm)	Gap Width (mm)	Seal Depth (mm)	Backing Material	Seal	FRL
200	11	10	Gorilla PEF	Both Faces	-/240/240
200	31	20	Gorilla PEF	Both Faces	-/240/180
100	33	20	Gorilla PEF	Both Faces	-/180/90
100	11	10	Gorilla PEF	Both Faces	-/180/120

9. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- For more detailed information, please refer to the SDS.

Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email info@soudal.co.nz.***

Last Updated: 15 April 2024

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	134 Kohia Drive	Phone: (07) 847 5540
	Horotiu	
	Hamilton 3288	Email: info@soudal.co.nz
	New Zealand	Website: www.soudal.co.nz