

Code	Description	Size	Colour
20255	Soudafoam SMX Genius	500ml	White

1. Description

Soudafoam SMX Genius is ready to use one component self-expanding and 100 % isocyanate free foam. Soudafoam SMX Genius is filled with HCFC- and CFC-free propellants which are not harmful for the ozone layer.

2. Characteristics

- Excellent stability (no shrinkage or post-expansion)
- High filling capacity
- Good adhesion on most materials (except PE/PP & PTFE)
- High insulation value, thermal and acoustic
- Very good bonding properties
- Freon Free (harmless to ozone layer & "greenhouse" effects)
- High thermal and acoustical isolation
- Not UV Stable

3. Technical Data

Basis:	SMX Polymer
Consistency:	Stable foam, thixotropic
Curing System:	Moisture curing
Skin Formation: (FEICA TM 1014)	13 minutes
Cutting Time: (FEICA TM 1005)	45 minutes
Free Foamed Density: (FEICA TM 1019)	Ca. 31 kg/m ³
Insulation Factor: (FEICA TM 1020)	37mW/m.K
Box Yield: (FEICA TM 1003)	500ml yields ca. 9 litres of foam
Joint Yield: (FEICA TM 1002)	500ml yields ca. 9 litres of foam
Shrinkage after curing: (FEICA TM 1004)	<3 %
Expansion after curing: (FEICA TM 1004)	<19 %
Compressive Strength: (FEICA TM 1011)	Ca. 6 kPa
Shear Strength: (FEICA TM 1012)	Ca. 23 kPa
Tensile Strength: (FEICA TM 1018)	Ca. 35 kPa
Elongation at Fmax: (FEICA TM 1018)	Ca. 68,9%
Temperature Resistance:	-40°C till +90°C (fully cured)

*This varies according to ambient conditions such as temperature, humidity, substrate etc

H1 insulation R-Value Calculations based on thickness of Gorilla Expanding Foam Range

Product	mW/m.K (TDS)	Thickness mm									
		50	60	70	80	90	100	125	140	200	220
Soudal Pro Expanding Foam Aerosol	29.7	1.68	2.02	2.36	2.69	3.03	3.37	4.21	4.71	6.73	7.41
Soudal Pro Expanding Foam Gun Grade	35.0	1.43	1.71	2.00	2.29	2.57	2.86	3.57	4.00	5.71	6.29
Soudal Pro Expanding Foam Click & Fix	32.0	1.56	1.88	2.19	2.50	2.81	3.13	3.91	4.38	6.25	6.88
Soudal Pro Expanding Foam Genius	37.0	1.35	1.62	1.89	2.16	2.43	2.70	3.38	3.78	5.41	5.95
Soudal Flexifoam Click & Fix	35.0	1.43	1.71	2.00	2.29	2.57	2.86	3.57	4.00	5.71	6.29
Soudal Flexifoam Genius	34.5	1.45	1.74	2.03	2.32	2.61	2.90	3.62	4.06	5.80	6.38
Soudafoam SMX Genius	37.0	1.35	1.62	1.89	2.16	2.43	2.70	3.38	3.78	5.41	5.95
Soudafoam FR HY Aerosol	34.0	1.47	1.76	2.06	2.35	2.65	2.94	3.68	4.12	5.88	6.47
Soudafoam FR HY Click & Fix	30.2	1.66	1.99	2.32	2.65	2.98	3.31	4.14	4.64	6.62	7.28
Soudal One Shot Expanding Foam	35.4	1.41	1.69	1.98	2.26	2.54	2.82	3.53	3.95	5.65	6.21

4. Applications

- Mounting and sealing of windows and doorframes
- Filling of cavities around pipes
- Connecting of isolation materials and roof constructions
- Application of a soundproofing layer on motors
- Improving thermal isolation in cooling systems

5. Packaging

500ml Genius canister (net)

6. Shelf Life

24 months in unopened packaging in a dry and cool storage place between 5°C → 25°C. Upright storage is recommended.

7. Building Product Information

Manufactured By Soudal NV
Distributed By Soudal Ltd

Relevant Building Code Clauses

- Clause B2 DURABILITY: Performance B2.3.1 (b) 15 years
- Clause E2 EXTERNAL MOISTURE: Performance E2.3.2.
- Clause F2 HAZARDOUS BUILDING MATERIALS: Performance F2.3.1.

Contribution to compliance With NZBC

Performance B2.3.1 (b): Assessment of durability to meet the NZBC is based on difficulty of access and replacement of the air seal, and the ability to detect failure of the air seal both during normal use and maintenance of the building when used as Air-seals (i.e. in dry, interior environments where the product is inaccessible, and completely sheltered from exposure to sunlight, chemicals, solvents and temperature extremes), they will remain serviceable for at least 15 years.

Performance E2.3.2: Complying with the requirements of NZBC Acceptable Solution E2/AS1 when installed in accordance with the design. Soudal maintains manufacturing and production records within its ISO9001:2015 Quality Management System, this product has performed successfully since it was introduced in 1999.

Performance F2.3.1: This product meets this requirement when used and applied in accordance with Soudal's product installation instructions and does not present a health hazard to people occupying or using the building. Refer to the Soudal Technical Data sheet and product Safety Data Sheet, soudal.co.nz for further information if required.

8. Application Instructions

Surfaces

Type: Various porous surfaces such as wood, concrete, stone and other materials commonly used in construction. Not suitable for PE, PP & PTFE

State: Clean, dry, free of grease and loose particles.

Application

Method: Aerosol can, shake thoroughly (at least 20 seconds) before application
Fill holes and cavities for 1/3 (as the foam will expand)
Repeat shaking regularly though application process

Canister temperature: +10°C → +30 °C
Ambient temperature: +5°C → +30 °C
Surface temperature: +5°C → +30 °C

Clean: Gorilla Expanding Foam Cleaner before curing
Repair: Soudafoam SMX Genius

Pre-treatment: Moisture in the air or the substrates will cure the adhesive, which will foam slightly. Slightly moistening the substrates will speed up the cure and increase the filling properties of the adhesive. Adhesion to metal batons is determined by surface preparation. An initial wipe with Gorilla 696 Surface Activator is required.

Limitations

- Soudafoam SMX Genius can be applied to a wide variety of substrates. Due to the fact that specific substrates may differ from Supplier to Supplier, Soudal recommends preliminary compatibility tests.
- Soudafoam SMX Genius is not UV-Resistant.

Remarks:

- Always moisten surfaces in order to improve curing and cellular structure
- Cured Soudafoam SMX Genius must be protected from UV-radiation by painting or applying a top layer of sealants (silicone, MS Polymer, etc)
- For the filling of large volumes apply product in layers and moisten between each layer
- Always store canister with the valve pointed upwards

Soudal recommends preliminary compatibility tests on surfaces on which SMX Foams have not been applied previously.

9. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- Wear gloves and safety goggles.

Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email info@soudal.co.nz.***

Last Updated: 11 November 2025

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	134 Kohia Drive	Phone: (07) 847 5540
	Horotiu	
	Hamilton 3288	Email: info@soudal.co.nz
	New Zealand	Website: www.soudal.co.nz